

Europäisches Patentamt European Patent Office Office européen des brevets

(1) Publication number:

0 296 619 Δ1

(12)

EUROPEAN PATENT APPLICATION

- (21) Application number: 88110125.7
- (1) int. Cl.4: F01L 3/02 , B23P 15/00

- ② Date of filing: 24.06.88
- Priority: 25.06.87 JP 97534/87
- Date of publication of application: 28.12.88 Bulletin 88/52
- Designated Contracting States: DE FR GB IT

- (P) Applicant: Kawasaki Jukogyo Kabushiki Kaisha
 - 1-1 Higashikawasaki-cho 3-chome Chuo-ku Kobe-shi Hyogo 650-91(JP)
- (2) Inventor: Nishiyama, Yukio 2-2-2, Havashizaki-cho Akashi-shi Hyogo(JP) Inventor: Fujioka, Junzo 335-33. Shimizu Uozumi-cho Akashi-shi Hyogo(JP) inventor: Hino, Haruki 3-1-43, Kaminotani Suma-ku Kobe-shi Hyogo(JP) inventor: Miyashita, Takuya 1-13-28-510, Tanaka-cho Higashinada-ku

Kobe-shi Hyogo(JP)

- Representative: Klunker . Schmitt-Nilson . Hirsch Winzererstrasse 106 D-8000 München 40(DE)
- @ Composite valve for reciprocating engines and method for manufacturing the same.
- @ A composite follow valve for internal combustion engines such as an intake and an exhaust valve and the method for producing the same are disclosed. The valve is produced by integrating into the whole a valve head portion (2) molded from a lightweight, heat-resistant material selected from a group of titanium alloys and titanium-aluminium alloys, a stem portion (3) molded from a high-strength alloy steel, made hollow inside to reduce weight, and a stem end portion molded from a hard material selected from a group of martensitic stainless steel, slilcon nitride and silicon carbide ceramics.

Since the different materials of the separate valve components are selected to meet the requirements of their particular functions and operating condition under which they are placed. Also, because of this separate arrangement, the valve can be produced at a relatively reduced cost, since the use of expensive materials is saved. Furthermore, the valve is molded, not in a whole body, but in separate components, there is no use for expensive isothermal forging machines as in the case of prior art production methods.



EP 0 296 619 A1

COMPOSITE VALVE FOR RECIPROCATING ENGINES AND METHOD FOR MANUFACTURING THE SAME

BACKGROUND OF THE INVENTION

1) Field of the Invention:

The present invention relates to a composite hollow valve for reciprocating engines such as an intake or exhaust valve. This invention also relates to a method for manufacturing the same.

2) Description of the Prior Art:

An internal combustion engine is required to have its intake and exhaust valves made lightweight to enhance responsibility and parformance at low speed ranges. Various development have so far been proposed along this line. One such an example is disclosed in published Jepanese patent application 81-229 907 by the same applicant as this invertion, which teaches valve drive system parts including titanium aluminides intake and exhaust valves. This prior art relies upon the excellent properties of titanium-au aluminides such as a low specific gravity equivalent to 48 to 61% of that of steel and oxidation resistance at high temperatures.

Production of a titanium aluminides engine valve such as an intake or exhaust valve consists in, first, providing a titanium aluminide billet as by argon arc melting, plasma arc melting, or vacuum arc melting method and then is formed into shape by precision casting, isothermal forging, extrusion, hot isostatic as press, with, if desired, suitable thermal treatment and machining work depending on the type of the part beling mamulactured.

Different parts of an engine valve including a valve head, stem, stem end are required to have a different set of properties from one another for desired valve performance as a whole. For example, a valve head portion must be highly heat-resistant while increased mechanical strength is one of the requirements so for valve stem portions. On the other hand, a valve stem end is required to have abrasive resistant properties.

Therefore, producing the whole parts of the engine valve from expensive titanium aluminides would not be sald an advantageous manufacturing method in the sense of effective material use.

Furthermore, the forming of an engine valve in integrated whole by isothermal forging method presents 3 a difficulty in the forging of a titanium aluminides, as an example, having an essential characteristics of a tough working, and, still furthermore, requires a skilled experience in a special forging technique even through the forming is available.

The present invention has been proposed to eliminate the above-mentioned drawbacks of the conventional engine valves.

It is therefore an objective of the present invention to provide a composite hollow engine valve for internal combustion engines such as an intake or exhaust valve which can be manufactured at a low cost while to a weight equal or substantially lighter than those prior art engine valves of comparable capacity and size.

It is also another object of the present invention to provide a method for producing such engine valves.

SUMMARY OF THE INVENTION

The above and other objectives, features and advantages of the present invention are achieved by integrating into a whole body the separate parts of an engine valve, manufactured from a different material from one another; the valve head portion from a lightweight, heat-resistant material such as titanium alloys and titanium alluminides, the stem portion from any known substantially high strength alloy steel, made hollow inside to reduce weight, and the stem end portion from a material with increased hardness.

Since the engine valve of the present invention is produced by integrating its separate components

EP 0 296 619 A1

made from selected materials to meet their required respective required properties in operation, the everall production cost can be relatively low, without giving unwanted, hence costly properties to each valve part, compared with conventional engine valves. In addition, since the valve is fabricated, not in a whole body, but in separate components, there is no need for expensive isothermal forging machines as in the case of 5 producing internal combustion engine valves made of titanium autimides.

In addition, since the engine valve of the present invention has its head portion made from stantion alloys or titunion aluminides, with its stem portion being made hollow inside, the overall valve weight is likely to be smaller, or at least, no more than that of internal combustion engine valves made of titunion

The table presented below compares the weight of an exhaust valve produced in accordance with the present invention with a typical conventional exhaust valve of comparable size and capacity, to be concrete, with a head diameter of 20 mm and a stem length of 90 mm for a 900 oc engine.

A kind of an exhaust valve

Part Name	Material	•	Weight	(gr.)
Composite F	ollow Exhaust V	alve of the	Present I	nvention
Head	Titanium Alumn		5.0	
Stem	Chromium-Molyb	denum Steel	9.0	
Stem end	Martensitic St	ainless Stee	1 2.0	
Overall weight			16.0	
Conventiona	l One-Piece Exh	aust Valve		
All parts	Heat-Resisting	Steel	32.0	

3

40

50

It will be apparent from the above table that the present invention can reduce overall valve weight by shalt.

Reduction in valve weight would also contribute to minimizing valve vibrations in engine operation.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is an overall view of one embodiment of a composite valve for internal combustion engines according to the present invention;

Figure 2 is a cross-sectional view of the valve of this invention showing the joint between its head and stem portion;

Figure 3 is a cross-sectional view of the engine valve of this invention showing the joint between the stem portion and stem end portion; and

Figure 4 is a side view of a composite valve for internal combustion engines showing the manufacturing methods according to the present invention.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

Freferred embodiments of the composite hollow valve for internal combustion engines according to the present invention will be described in hull detail in conjunction with the accompanying drawings. Referring first to Figure 1, a valve 1 for internal combustion engines, which should hereinafter should be

meant to refer to both an intake and an exhaust valve, comprises a head portion 2, a stem portion 3, and a

stem and portion 4, each produced from a different material, formed into shape through separate manufacturing process, with some machining and other treatment operations being added as necessary, and integrated into a whole.

The head portion 2 may, as can best shown in Figure 2, be formed with a closed connection hole 5. 5 The hole 5 is provided to fittingly receive therein a tail end of the stem portion 3. The fitting may be by any suitable conventional method such as shrinkage fit, cold fit, brazing, or other mechanical fitting in conjunction with or without one of two of these methods in combination.

The stern portion 3 is constructed hollow inside to reduce weight. A core portion 6 is inserted into the hollow of the stern portion 3 at its top end, which is firmly secured in position as the above.

The head portion 2 may preferably be produced from a lightweight, heat-resistant material such as titanium alloys or titanium aluminides. The stem portion 3 may preferably be made hollow, manufactured from a low alloy steel such as chromium-molybdenum steel or a titanium alloy, processed for abrasive resistance by Tuffride or molybdenum flame spraying. Also, the stem end portion 4 may preferably be produced from a very hard material such as materistic steel or ceramics.

The foregoing titanium aluminides for the head portion 2 may be an intermetallic compound of titanium and aiuminum such as TRIA and TlpAI, preferably with the mixture of one or more additives such as Ni, Nb, W, V, Mn, and B to enhance the good properties of the material. In more detail, the most desirable materials include, as TlAI, Ti-36A1 and Ti-36A1-5Nb as well as (Signers being in percentage by weight).

To produce a valve head portion 2 according to the present invention, the mother material is produced from one of the above-mentioned materials by argon are melting, plasma are melting or vacuum are remelting, and then is formed into shape by precision casting, isothermal forging, extrusion, hot isostatic press, with, if desired, suitable thermal treatment and machining work.

Among the foregoing titanium-aluminides for the head portion 2, TisAt alloys provide increased formability while TAt alloys being excellent in resistance to high temperatures. Thus, selection of materials by the valve designer may depend on the purpose for or operating condition under which his valve to be developed is intended.

Where both the head portion 2 and the stem portion 3 are manufactured from the same material of titanium alloy, a concrete example of this material may be Ti-6A1 -2Sn-4Zr-2Mo.

When the head portion 2, the stem portion 3 and the stem end portion 4 of the intake or exhaust valves of an internal combustion engine are each produced, according to the present invention, from a different material that meets their particular requirements of operation, the production cost for the valve as a whole would be reduced, without reducing properties of the individual parts hence possibly correspondingly costino, properties, compared with conventional engine valves.

In addition, the valves can be manufactured in divided sections, the conventional employment of large forging machines is eliminated, with a resultant further reduction in production cost. Furthermore, the overall weight of the intake and exhaust valves thus produced can be smaller than, at least equal to that of conventional engine valves since their head portions 2 are made from a lightweight material with a low specific gravity such as titantum alloys or itanium aluminides, with the stem portions 2 being built in hollow

Referring to their Figure 4, the method for manufacturing a composite hollow valve for internal combustion engine will be described. The head portion 2 of the valve is formed in its center with a closed connection hole 5. A number of circumferential grooves 5a are cut in the Inside wall of the hole 5, which is closed at its lower and by a bottom wall 5b.

The stem portion 3 has its lower end made larger in diameter than the rest of its body. The stem portion 3 is inserted into the hole 5.

With the stem portion 3 inserted into the hole 5 of the head portion 2, the joint is exposed to uniform heating by a high-frequency heating device? 7. When the temperature of the joint is increased to a predetermined high level, pressurized inert gas is supplied from the opposite open end of the stem portion 3 through its holicy portion, so that the gas inside undergoes an instantaneous thermal expansion, causing the endarged end of the stem portion 3 to expand outwardly against the inside wall of the hole 3 in the head

Then, a stem end portion, not shown, is fitted to the opposite end of the stem portion 3, and the assembled valve may be treated with the necessary steps of machining work and treatment to make it an si intake or exhaust valve.

The method according to the present invention can shorten the production of composite valves for Internal combustion engines since joining the components can be achieved in a short period of time. Also, the method can insure connection between the parts.

FP 0 296 619 A1

Claims

35

4n

- 1. A composite valve for internal combustion engines, comprising a head portion (2) having in its center a closed hole (6) for fitting connection, said valve head being adapted to close and open the port of a cylinder head, a valve end adapted to receive linear titrust for valve operation, and a stem portion (3) enterconnecting said valve end with said valve head, said stem portion (3) being fitted into said hole with its one end while as a stem end portion (4) being secured to said stem portion thereby assembling a whole valve body.
- A composite valve as set forth in Claim 1, wherein said head portion (2) is manufactured from a substantially lightweight, heat-resisting alloy material.
 - 3. A composite valve as set forth in Claim 1 or 2, wherein said stem end portion (4) is manufactured from a substantially hard material.
 - 4. A composite valve as set forth in any of the claims 1-3, wherein said stem portion (3) has an axially hollow bored therein and is manufactured from a high strength alloy material,
- 5 5. A composite valve as set forth in Claims 1-4, wherein said head portion (2) is manufactured from a material selected from a group of titanium alloys and titanium-aluminides.
 - 6. A composite valve as set forth in Claims 1-5, wherein said stem end portion (4) is manufactured from a material selected from a group of martensitic stainless steel, silicon nitride, and silicon carbide ceramics.
- 7. A composite valve as set forth in Claims 1-6, wherein said stem portion (3) is manufactured from a material selected from a group of alloy steels, soft nitrided titanium alloys, and titanium alloys coated with molybdenum by thermal spraying.
 - 8. A method for manufacturing a composite valve for internal combustion engines, comprising the steps
- providing a head portion (2), a stem portion (3) with an axial hollow formed therein, and a stem end portion, boring an axial closed hole (5) in the center of said head portion (2),
 - forming a number of circumferential grooves (5a) in the inside wall of said hote (5), connecting said stem portion (3) with said head portion (2) by inserting one end of said stem portion (3) into said hote (5).
- exposing said head portion (2) with said end of said stem portion (3) being held inserted into said hole (5) to heating by heating means,
- supplying pressurized inert gas from the opposite free end of said stem portion (3) through said hollow, while said head portion (2) being heated, until said joined end of said stem portion (3) to swell outwardly in thermal expension within said hole (5) to pressure if therebetween, and
- securing said stem end portion (4) to said free opposite end of said stem portion (3).

FIG.I



FIG.2




FIG.3





FIG.4



EP 88 11 0125

	DOCUMENTS CONS	SIDERED TO BE RELEVA	NT	· ·
Category	Citation of document with of relevant	indication, where appropriate, passages	Relevant to claim	CLASSIFICATION OF TE APPLICATION (Int. Ct. 4)
Y A	GB-A- 187 119 (B * Page 2, lines 45	ARRS) -70,75-77; figure 1 *	1 3,4,8	F 01 L 3/02 B 23 P 15/00
Υ	FR-A-2 532 360 (S * Page 3, lines 21	ULZER) -29; page 6, 1ines	1	
A	1-0 "		2,4	
A	GB-A- 538 654 (C * Page 1, lines 8- page 2, line 4; fi	15: page 1. line 77 -	1,2,4,7	
A	EP-A-0 091 097 (N * Page 6, line 3 - figures 2,3 *	ISSAN) page 7, line 24;	1-4,8	
A	253 (M-512) 2309 .	F JAPAN, vol. 10, no. 29th August 1986; & NDA MOTOR CO., LTD)	5,7	
	* Abstract *	•		TECHNICAL FIELDS SEARCHED (Int. Cl.4)
1	US-A-4 359 022 (N/ * Column 1, line 59 column 2, lines 36	- column 2. line 2:	6	F 01 L B 23 P
A	FR-A- 918 309 (JE * Page 1, lines 28-	EUDI) -38; figures 1-3 *	3	
	The present search report has b			
THE	HAGUE	Date of completion of the search 04-10-1988	LEFEE	Examiner BVRE L.J.F.
X : partie Y : partie docum A : techn O : non-	ATEGORY OF CITED DOCUME tularly relevant if taken alone cularly relevant if combined with an ment of the same cartegory cological background written disclosure mediate document	E : earlier patent de	ple underlying the in scument, but publish late In the application for other reasons	ivention hed on, or